

TECHNICAL DATA SHEET

SEÑACRIL NEGRO ANTIDESLIZANTE **REF. 3200A**

ROAD MARKING

DESCRIPTION

Acrylic non-skid black paint for road marking.

SPECIAL PROPERTIES

- Easy application
- Resistant to alkali due to its unsaponifiable property
- Machinery easy to clean.

USE SCOPE

- Good roadholding over bitumen and repainted surfaces.
- Paint for road marking over asphalt and concrete pavements due to its unsaponifiable property.
- Aimed to road marks removing.

TECHNICAL DATA

CONSISTENCY	UNE 48076	95 ± 10 KU
SPECIFIC GRAVITY	UNE 48098	1,65 ± 0.02 gr/cm ³
DRYING TIME	UNE 135202	15 minutes
COLOUR	UNE 48073/2	(x, y) inside polygon colour.
LUMINANCE FACTOR	UNE 48073/2	$\beta \leq 0.05$
NON VOLATILE CONTENT	UNE-EN 12802	77 ± 2 %
STORAGE STABILITY	UNE 48083	Change of consistency ≤ 5 KU No skinning, nor hard settlements.
BINDING CONTENT	UNE-EN 12802	14 ± 5 %

This product is in accordance with the Spanish Standard **UNE 135200-2** in force, which specify particular values of the characteristics defined in the European standard **UNE-EN 1871**.

It allows fulfill the requirements of the European standard **EN 1436**, when applied together correctly with micro glass beads and anti-skid aggregates.

TECHNICAL DATA SHEET

SEÑACRIL NEGRO ANTIDESLIZANTE

REF. 3200A

ROAD MARKING

APPLICATION

It can be applied by roller, spray gun or airless spray gun machine .

DILUTION

Depending on weather conditions and the application system , it can be diluted between 1% or 2% with superfast solvent "AA80" or superfast solvent "IH80".

APPLICATION CONDITIONS

Do not apply with temperatures below 5°C or over 40°C.

INSTRUCTIONS FOR USE

- Apply over dry and clean surfaces, free from dust, oil or dirtiness. If the surface was already painted, eliminate all the remains.
- In new concrete soils, rests of whitewash and curing agents can seriously damage paint adherence, so they must be removed immediately
- Mix well the content of the pail to homogenise the product.

DOSAGE

Depending on the pavement uniformity, it is recommended a dosage of 720 gr/ m²

EQUIPMENT CLEANING

Materials and equipment must be cleaned immediately after use with thinner for acrylic products "AA80".

STORAGE STABILITY

- Outdoors lengthy storage is not convenient, neither the product to be subjected to great temperature changes (5°C – 40°C).
- Keep away from freezing weather.
- It is recommended to use the product within one year after the fabrication date.

CAUTIONS

- Please consult the product label and security data sheet. For further information please consult the Technical staff members of our Commercial Department or visit our web:

www.pinturasralva.com

PRESENTATION

Homologated metallic pails, net weight 30 kg. Pallets of 36 pails (1080 kg – 1145 kg including packing).

Pallet measures: 0.90 x 1.20.