

TECHNICAL SHEET

RALVAEXPRESS-REF.AA52

ENZANMIEIS

DESCRIPTION:

- Fast drying synthetic enamel.
- Brilliant finish.

SPECIAL PROPERTIES:

- Quick drying.
- In case of need can be dried in oven at 60 ° C maximum

USE SCOPE:

- Aimed to the general industry ,for steel surfaces and in case a fast drying is needed.

TECHNICAL DATA:

FINISH:	BRILLANT
COLOUR	WITHE (100) AND COLOURS UNDER REQUEST
SPECIFIC GRAVITY:	1250 ±50 gr/l (20°C) (DEPENDS ON COLOURS)
WEIGHT SOLIDS:	59 ± 3 %
PERFORMANCE:	9 – 10 m ² /kg
TACK DRY :	< 20 minutes
TOTAL DRY:	< 40 minutes

APPLICATION DATA:

APPLICATION:	Airless gun, roller
SOLVENT:	FAST SOLVENT "AA80"
DRY FILM THICKNESS:	30 microns
REPAINT TIME:	12 hours

INSTRUCTIONS FOR USE:

- Apply over dry and clean surfaces, free from dust, oil or dirtiness. If the surface is already painted, eliminate all the remains.
- Please prepare before the substrate with a primer antioxidant PRIMER S / R - "AA20" or ZINC PHOSPHATE PRIMER - "AA22".

FOOTNOTE:

- Performance mentioned has been calculated over non-absorbents smooth surfaces .
- Recommended dry film thickness is per coat and hand applied.



RALVA, SA reserves the right to update and modify any specific technical data according to the legislation in force. The information, prescriptions and use given, are based in Ralva's knowledge about its products in normal situations and using them correctly. The user must verify the suitability of the product attending to the use intentions, the surface and the real conditions of the appliance place.

TECHNICAL SHEET

RALVAEXPRESS-REF.AA52

EN
AMBIENTES

APPLICATION CONDITIONS:

- Do not apply during extreme cold and hot temperatures

EQUIPMENT CLEANING

- Materials and equipment must be cleaned immediately after use with thinner for acrylic products "AA80".

STORAGE STABILITY:

- Outdoors lengthy storage is not convenient, neither the product to be subjected to great temperature changes (5°C – 40°C).
- Keep away from freezing weather.

CAUTIONS:

- Please consult the product label and security data sheet. For further information please consult the Technical staff members of our Commercial Department or visit our web:

www.pinturasralva.com



RALVA, SA reserves the right to update and modify any specific technical data according to the legislation in force. The information, prescriptions and use given, are based in Ralva's knowledge about its products in normal situations and using them correctly. The user must verify the suitability of the product attending to the use intentions, the surface and the real conditions of the appliance place.